

# Monogal-F

**M**onogal F extruded polycarbonate sheet offers high impact resistance with enhanced UV and fire-resistant properties. Monogal F has superior clarity, is half the weight of glass, and is virtually unbreakable. Monogal F sheets are ideal for applications requiring high temperature resistance including automotive, aerospace, electrical housings and covers, lighting, machinery and safety and construction.

*Low Flammability  
Solid Polycarbonate  
Sheets*

## Product Information

Gauges	.080" - .236"	
Standard Sizes	Length: 96"	Widths: 48", 60", 72"
Tolerances	Gauge $\pm 5\%$ (Gauges: .080" - .236")	Width & Length, Standard: .000" (Minimum) .250" (Maximum)
Availability	48" - Generally Common Stock	60" / 72" - Contact customer service for availability
Packaging Information	Available in 1/2 pallet and full pallet quantities	
Masking Information	Standard Monogal PE film Two (2) sides	Additional Monogal-F identification strip

General Properties	Method	Units	Value
<b>Physical</b>			
Density	ASTM D 792	g/cm <sup>3</sup>	1.2
Light Transmission (depending on thickness)	ASTM D 1003	%	81-90
Refractive index	ASTM D 542		1,585
<b>Mechanical</b>			
Tensile Strength at yield	ASTM D 638	PSI	9,300
Tensile Modulus	ASTM D 638	PSI	335,620
Elongation at break	ASTM D 638	%	>100
Flexural Strength	ASTM D 790	PSI	13,450
Flexural Modulus	ASTM D 790	PSI	338,690
Rockwell Hardness	ASTM D 785	M-Scale	70
Impact Resistant – Izod Notched @0.125"	ASTM D 256	ft. lbs/in	18
<b>Thermal</b>			
Heat Deflection temperature under load of 264 PSI	ASTM D 648	°F	270
Vicat Softening temp (50N)	ASTM D 1525	°F	290
Coefficient of Thermal Conductivity	ASTM D 177	BTU-in/hr-ft <sup>2</sup> • °F	0.2
Coefficient of Linear Thermal Expansion – parallel	ASTM D 696	in/in °F	3.8 • 10 <sup>5</sup>
<b>Flammability</b>			
Flame Class @.080"	UL-94		V-0
FAA Flammability	FAR 25.853		
.080" - .236"	Part 1. a (i) - 60 sec		Pass
.080" - .236"	Part 1. a (ii) - 12 sec		Pass
<b>Electrical</b>			
Volume Resistivity	ASTM D 257	$\Omega \cdot \text{cm}$	8.2 • 10 <sup>16</sup>
Surface Resistivity, dry	ASTM D 257	$\Omega$	6 • 10 <sup>15</sup>
Dissipation Factor 1Mhz	ASTM D 150		0.009
Dissipation Factor 100Mhz	ASTM D 150		0.0006

**Polygal Inc. | plazit-polygal.com | 1100 Bond Street, Charlotte, NC 28208 | 1-800-537-0095**

*The Plazit-Polygal Group is a leading world supplier of plastic sheets, bringing together expert professionals committed to providing high quality & reliable products & solutions, designed to meet our customer's exact needs.*